


WINDY'S ANNIE

AFD: 22.5 μ
SD: 4.6 μ
CV: 20.5 %
CF: 93.8 %
Curve: 38.1 Dg/mm
Min: 21.6 μ
Max: 23.4 μ
Staple: 70.0 mm

% of Fibers



Alpaca Fiber Testing USA

Fiber Diameter (microns)

WINDY'S ANNIE

AFD: 22.5 μ
SD: 4.6 μ
CV: 20.5 %
CF: 93.8 %
Curve: 38.1 Dg/mm
Min: 21.6 μ
Max: 23.4 μ
Staple: 70.0 mm

