


WINDY'S HENRY

AFD: 27.3 μ
SD: 4.9 μ
CV: 17.9 %
CF: 77.3 %
Curve: 29.0 Dg/mm
Min: 24.2 μ
Max: 29.1 μ
Staple: 95.0 mm

% of Fibers



Alpaca Stats Inc. Testing USA

Fiber Diameter (microns)

WINDY'S HENRY

AFD: 27.3 μ
SD: 4.9 μ
CV: 17.9 %
CF: 77.3 %
Curve: 29.0 Dg/mm
Min: 24.2 μ
Max: 29.1 μ
Staple: 95.0 mm

