


WINDY'S HATTIE

AFD: 20.9 μ
SD: 4.7 μ
CV: 22.5 %
CF: 96.0 %
Curve: 30.0 Dg/mm
Min: 19.3 μ
Max: 22.9 μ
Staple: 80.0 mm

% of Fibers

Alpaca Fiber Testing USA



Fiber Diameter (microns)

WINDY'S HATTIE

AFD: 20.9 μ
SD: 4.7 μ
CV: 22.5 %
CF: 96.0 %
Curve: 30.0 Dg/mm
Min: 19.3 μ
Max: 22.9 μ
Staple: 80.0 mm

